



for windows



for doors



store and transport
in a frost free area



store in a cool place



cleaning of
equipment with
water



Opened containers
must be properly
closed

Kodrin WV 472

Product description Elastic sealing matter for parapet V-joints (max. radius 3 mm), especially V-joints in the parapet areas of wooden windows and doors, against the ingress of moisture.
Can be used on translucent and opaque paint systems, interior and exterior.
Parapet joints on windows and doors are joints where the haunches i.e. endgrain meets the rail and are normally not longer than 10 cm.
The sealing matter is not suitable for other construction joints.
- a neutral odour
- easy to apply

Colour Semi transparent

Binder type Special polymer dispersion

Packaging 320 ml cartridge

Processing The sealing matter is applied in the joint with the help of a skeleton gun into the clean dust free parapet V-joint and consequently wiped clean with the finger. It is recommended to wear a light glove.

Consumption Approx. 50 ml/running metre V-joint.

Thinning Do not thin down

Application temperature 15-25 °C for substrate, air and material at approx.60 % R.H.

Drying times The drying process of the materials can be delayed depending of applied wet film thickness and when using timber with a high extract contents and drying in damp/cold weathering conditions. During the drying process one should ensure for adequate airing and temperature conditions.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

At normal climate 23 °C/50 % R.H. DIN 50014

Recoatible: after fully dried . If possible over night, earliest after 2 hours waterborne

Cleaning of equipment Clean directly after use with water or washing up liquid or with ST 830* (cleaning agent).

Storage Minimum storage stability of sealed containers at room temperature: 1 year. Opened cans must sealed correctly! Store in a cool but frost-protected area.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

VOC guideline Out of scope.

General instructions The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 C).

For use in a technical industrial companies and exclusively released for Sikkens systems recomondations.

Coating recommendation The sealing matter is applied after complete drying of the primer and midcoat on a clean, dust and grease free V-joint. Do not use a soapy substance. After the drying of the sealed joint, it can be coated with all following mid and finishing systems.

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.