



TIKKURILA OPTIVA CERAMIC SUPER MATT [3]

DESCRIPTION

The newest generation, waterborne, latex, acrylic-composite paint worked out with use of modern technologies: ceramic (guarantee high mechanical durability of the surface) and encapsulation (increases the barrier properties of painted surface). It is intended for decorative painting of walls and ceilings inside residential, office and public use buildings and in schools and health care premises (hospitals, schools, kinder-gardens), workhouses and production plants and also food industry without direct contact with food*. Forms beautiful, washable matt finish. Rich colors, the palette of colors over 13 thousand colors, is the best guide for your interior. Let yourself be inspired.

RECOMMENDED USES

Painting of gypsum boards, gypsum, cement-lime plasters, decorative painting of concrete substrates as well as for renovation of old coatings. Product may be used on small wood and metal surfaces, before application surface should be primed with suitable primer (Tikkurila Everal Primer, Tikkurila Everal Corrostop, Tikkurila Rostex Super Akva).

PRODUCT FEATURES

CERAMIC TECHNOLOGY – unique arrangement of ceramic and functional fillers:

1. High mechanical durability of the surface to glossy spots and traces after wiping the surface, etc.
2. Expressive depth of colour especially attractive for paints in deep matt.
3. Exclusive anti-reflex, deep matt finish, uniform independently of the watching angle.

ENCAPSULATION TECHNOLOGY

1. Very good hiding power
2. Increased durability of the paint surface to stains and dirt**
3. Increased durability of the paint surface to dirt and dust
4. Decreased migration of salts effect (lower migration of salts in old buildings, churches, museums, etc.)

OPTIMAL AND DURABLE EFFECT

1. Unique ability to regenerate matt surface by gently wiping the wall with dry or wet cloth, thanks to specially used modern combination of waxes the wall regenerate it's matt surface.
2. Uniform and easy to achieve paint surface structure.
3. Highest wet scrub durability – 1st class (PN-EN 13300)
4. Durability of colour in long period of time
5. Beautiful, deep matt finish.
6. Innovative tinting system Avatint.

FOR HEALTH AND ENVIRONMENT

1. Product doesn't contains volatile organic compound: zero VOC***
2. Eco-friendly recipe and the highest quality certified Ecolabel.
3. Recommendation from Polish Allergy Society (PTA)****.
4. Raw materials used in paint production according to European parliament decree REACH, which aim i to assure high level of health and environment protection.
5. Paint fulfill the VOC requirement in BREAM International certificate system*****.
6. A+ class on account of low emission from the coat according to French norms.
7. We don't add formaldehyde in production process.

EASY APPLICATION

1. Non-dripping formula.
2. Very good adhesion to the surface.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



TIKKURILA OPTIVA CERAMIC SUPER MATT [3]

3. Easy spread of paint.
4. Optimal drying time.

** it is recommended to remove the stains not later than 15 minutes after getting the dirt on the paint surface.

*** according to norm: PN-EN ISO 11890:2

**** recommendation of Polish Allergy Society (PTA) concerns product after the painted surface is fully dry and the room has been thoroughly ventilated.

***** acquaint Yourself with details in Producer Declaration concerning BREEAM International system.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

TIKKURILA OPTIVA CERAMIC SUPER MATT [3]

TECHNICAL DATA	
Base paints	A BASE, C BASE
Colour Shades	Colours from colour cards Tikkurila Symphony, Tikkurila Deco Grey, NCS, RAL. Pallet of shades for over 13.000 colours.
Gloss	Full matt. According to norm: PN-EN 13300 gloss [3].
Binder	Styrene acrylate
Coverage	Up to 16 m ² /l max. with one coat. The coverage depends to a large degree on such factors as absorbability, substrate texture, application method and colour.
Can sizes	A BASE: 0.9 l, 2.7 l, 9 l C BASE: 0.9 l, 2.7 l, 9 l
Thinner	Water. If necessary thin up to 5% with water.
Application method	Brush, roller, spray (nozzle: 415, pressure: 150 bar).
Drying time (23°C and 50% relative air humidity)	At temperature +23°C, relative air humidity 50% the paint needs approx. 1 hours to dry. The interval between application of subsequent coats must be at least 4 hours. In lower temperatures and higher humidity the time between the application of next coat might be longer.
Density (kg/l)	Base A – approx. 1,34, Base C – approx. 1,28 (depend on colour).
Wet scrub resistance	The highest – 1st class (according to norm: PN-EN 13300:2002), (PN-EN ISO 11998:2007P). In case of dirt on the surface for cleaning might be used water with delicate cleaning detergent.
Light resistance	Durability test for irradiation of the surface with UVC germicide lamps – the look of the surface and the shade didn't change after 8 hrs. of irradiation.
Weight solid (%)	54-56
Special feature	Surface regeneration: imperfections of the surface, which was made during using of the surface can be eliminated after gently wiping them with dry or wet cloth.
VOC	Cat. A/a. The product contains a minimal amount of volatile organic compounds below 1,5 g/l (below the applicable standard). Since 2010 permissible VOC content is less than 30 g/l.
Storage	The product must be transported and stored in containers, which protect it against influence of atmospheric conditions. The storage and transport temperature must be between +5°C and +25°C. Protect the paint against frost. Close tightly the packaging immediately after use. Tightly closed packaging should be stored in room with temperature not lower than +5°C and not higher than +25°C, protect from frost and direct sunlight.



TIKKURILA OPTIVA CERAMIC SUPER MATT [3]

Hygienic certificate	YES
-----------------------------	-----

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

TIKKURILA OPTIVA CERAMIC SUPER MATT [3]

APPLICATION INSTRUCTIONS

Application conditions

All surfaces intended for coating must be dry, air temperature may not be lower than +5°C and not higher than +25°C, relative air humidity below 80%.

Surface preparation

Unpainted surfaces:

New plaster and concrete substrates can be painted after 4 weeks of seasoning. Clean these surfaces from dust and dirt, smooth out irregularities and losses with putty. Gypsum boards, cardboards and putty may be painted after they are fully dry. In case when unevenness of the surface is considerable, the wall should be even with leveling mortar and afterwards apply on the whole surface smooth putty. In case of small unevenness you may apply smooth putty at once. The use of above mentioned mortars and putty should be done according to data sheets of these products. Machine plaster with visible glossy sinter surface should be sanded and clean from dust. Then apply one coat of Tikkurila Optiva Primer, as finishing coat apply two coats of Tikkurila Optiva Ceramic Super Matt [3].

Previously painted surfaces:

Wash the surface before coating and remove grease and dirt and loose and flaking fragments of old coat. Sand glossy surfaces and smooth out irregularities and losses with putty. Paint with gloss grade: satin, semi-matt, semi-gloss and gloss should be sanded on the whole surface before final dusting. For sanding use sanding paper with grain 150-200. Prime the whole of substrate with Tikkurila Optiva Primer. Paint twice with the Tikkurila Optiva Ceramic Super Matt [3].

Surfaces painted with glue or lime paint:

Remove thoroughly the lime or glue paint. Clean the surfaces from dust and dirt, smooth out irregularities and losses with putty. Then apply one coat of Tikkurila Optiva Primer, as finishing coat apply twice the Tikkurila Optiva Ceramic Super Matt [3] paint. In case of loose substrate prime with impregnate Tikkurila Suprabilit.

Notice: It is recommended to check if the used putty is strong and stable surface – if after delicate hand wipe the putty is falling or leave the dust on hand then it means that the surface is loose and it has to be primed with Tikkurila Suprabilit.

Top coating

Before application thin sufficient amount of paint from one production batch to avoid possible colour difference. Before painting stir the paint thoroughly. Depending on substrate porosity apply 2 coats of Tikkurila Optiva Ceramic Super Matt [3] with brush, roller or spray. For colours of particularly weak hiding power (marked within the tinting system) it may be necessary to apply additional coats. In case of applying colours marked in tinting system as weakly hiding (LH) and intensive colours from C base, it is recommended to use priming paint Tikkurila Optiva Primer tinted to a colour close to the colour of finishing paint. The painting tape should be removed immediately after painting, before the paint will dry. It is recommended to use ANZA painting tools.

Notice: Full resistance properties to wet cleaning, according to PN-EN 13300, coating achieves after 28 days from the end of painting.

In this technical data sheet, it is impossible to describe all aspects of the use of the product. In cases that are not described above, please contact the Technology Advisor. We will gladly provide you with detailed information related to a particular object.

Cleaning of tools

Before washing tools should be thoroughly wiped in order to remove as much paint. Clean tools with water immediately after the completion of the work.

Environmental and waste disposal

Do not pour liquid waste into drains. Liquid waste should be destroyed according to the local regulations for hazardous waste. Destroy liquid waste according to the local regulations for hazardous waste.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

After work and before breaks wash your hands thoroughly. If ventilation during spray application is insufficient use respirators or full face respiratory protective equipment, fitted with a filter absorbing dust P2 (II b). When painting wear appropriate protective clothing and gloves. Keep the paint out of reach of children. After application of paint in closed rooms ventilate until disappearance of smell and after that time the rooms are suitable for use. This product contains a biocidal product for the preservation of the product during storage. Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)), 1,2-benzisothiazol-3(2H)-one (BIT) and 2-methyl-2H-isothiazol-3-one (MIT). May produce an allergic reaction. Wear protective gloves. The Material Safety Data Sheet is available on Customer's request.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.