



spraying



for windows



for doors



limited dimension
stable wooden
constructions



stir before use



water thinnable



store and transport
in a frost free area



store in a cool place



cleaning of
equipment with
water

Rubbol WF 375

Product description Waterborne, opaque, gloss mid and finish coat for wooden constructions exterior and interior.

- high filling properties
- good leveling properties
- easy to apply
- good weather resistance
- sweat and saliva genuine (according to DIN EN 71, part 3)

Colour Various gloss levels can lead to varying appearances
White and colours from RAL, Sikkens 4041 Color Concept and NCS.

Gloss level Gloss

Binder type pure acrylic dispersion

Pigments Titanium dioxide as well organic and inorganic coloured pigments

Packaging 10 L

Processing Spraying

Wet film thickness: 2 X 150µm or 1 X 150 to max. 300µm.

It is recommended to apply translucent colours in two coats.

Consumption 150 - 300 ml/m², depending on applied wet film thickness per coat without losses.

Thinning If necessary with water max. 5 %.

Application temperature 15 - 25 °C for substrate, air and material at approx. 60 % R.H.

Drying times The drying process of the materials can be delayed depending of applied wet film thickness and when using timber with a high extract contents and drying in damp/cold weathering conditions. During the drying process one should ensure for adequate airing and temperature conditions.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 60 minutes

Recoatable: after approx. 4 - 6 hours waterborne

Cleaning of equipment Clean directly after use with water or washing up liquid or with ST 830* (cleaning agent).

Storage The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

VOC guideline EU limit value for this product Kat. (A/d): 150 g/l (2007)/130 g/l (2010). This product contains max. 80 g/l VOC.

General instructions The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 °C).

For use in a technical industrial companies and exclusively released for Sikkens systems recommendations.

With some wood species, especially some leaf woods, discolouration due to natural wooden extracts, can appear.

Relevant information System recommendation for semi stable wooden constructions:

Due to the high wood moisture changes in these type of constructions, only a medium build system can be recommended. The complete dry film thickness should not exceed 200µm. A midcoat is not needed.

The product reduces the discolouring caused by inhabitants. The effectiveness can be increased with use of a isolating base and midcoat.

The here mentioned coating system is only an example, other systems are possible.

All foreign materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Please observe the corresponding technical data sheets or seek advice from the Sikkens sales representative or contact the technical centre.

Coating recommendation The coating system can, after cleaning with the special cleaning agent, lightly sanded and dusted be recoated with the recommended solventborne maintenance product.
When coating leaf woods, we recommend the use of a pore filling midcoat.



System structure: Dimensional stable wooden constructions

Impregnation	Impregnation for the wood resistance class 3-5. Do not use more than one BPD-product in ONE system. Cetol WV 885 BPD+
Primer	Rubbol WP 194
Mid coat	Rubbol WM 270 Rubbol WF 375 Cetol WM 665
Top coat	Rubbol WF 375

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.